

TECHNICAL DATA SHEET

EU-100

EPOXY UNDERLAYMENT

MIL-D-3135 Type I CLASS 2

MIL-D-3135 Type II CLASS 2

Description

EU-100 is a three-component epoxy material consisting of a base resin; a hardener and aggregate used to level surfaces prior to installation of resin terrazzo's, polymeric deck coverings, linoleum, tiles or other similar pre-formed materials.

EU-100 will adhere to metal surfaces primed with epoxy primers, provided bonded to the subsurface. It will also adhere to wood, some plastic surfaces such as polyester or epoxy and well-cleaned concrete. On concrete surfaces, Underlay must be applied over tacky Bond Coat (BC-100).

Fire retardant in the cured state, **EU-100** is formulated and manufactured to meet the stringent requirements of MIL-D-3135 for fairing prior to application deck coverings.

Surface Preparation

- Existing deck covering must be 100% removed. It is imperative that surfaces to which deck covering is to be applied be thoroughly cleaned of all foreign matter such as dirt, oil, grease, wax, paint, rust, moisture, and other contamination before installation is begun.
- Preparation shall be by methods most feasible, such as grinding, sanding, or using needle point gun to expose bright metal. Concrete should be clean and sound prior to application. Consult surface preparation sheets available from American Safety Technologies for more detailed procedures.
- Remove all dust and other loose matter from the area. Clean deck free of remaining contaminants with an approved degreasing solvent.
- If exposed surface requires corrosion protection, apply MS-7C, MS-7CZ, or MS-10C Primer.

Mixing and Application

The packaged components are:

- Aggregate (50 lb. bag)
- Epoxy resins consisting of a base and hardener packages separately.

NOTE: To promote proper adhesion of underlayment, substrate must first be primed with BC-100 Bond Coat available from American Safety Technologies.

Additional Information Available: WWW.ITWAST.COM

Specifications

V.O.C.

- "0" lbs. per gal.
("0" grams/liter)

Pot Life

- 1 hour @ 70°F (21°C)

Dry Time

- 12 hours @70°F (21°C)

Estimated Coverage

- 25 sq. ft./kit
(1/4" thickness)

Flash Point

- N/A

Packaging

- 5 gallon kits

A. Bond Coat

1. Pour Part B into Part A and stir thoroughly for approximately three minutes. Scrape sides and bottom of can to insure complete mixing. Apply with brush and /or short nap roller to all surfaces where **EU-100** is to be applied. Avoid puddles.

2. Topping must be applied while Bond Coat is still tacky.

B. Underlayment

1. Pre-mix aggregate before mixing with catalyzed resin in Heavy Duty Mixer, J-7 or similar other mixing apparatus.

2. Mix resin by pouring Part B into Part A and stir thoroughly for approximately three minutes. Pour mixed resin into container with pre-mixed aggregate and mix approximately two minutes or until particles are wet.

3. Apply Underlayment directly over tacky Bond Coat at a minimum thickness of 1/8".

4. Apply Underlayment using standard cement finishing tools. Use low-level lighting to help avoid trowel marks.

5. Allow material to cure for a minimum of 6 hours or until hard.

6. Sand surface as may be necessary to make surface smooth. Clean up loose particles afterward.

Clean tools immediately after installation using an epoxy solvent such as xylene.

CAUTION

Read Material Safety Data Sheet before using this material.

Contains epoxy resins. Catalyst contains Amines. Use only with adequate cross ventilation. Keep away from extreme heat, sparks and open flame. Avoid prolonged breathing of vapors. For dizziness, seek fresh air. Toxic material. Avoid contact with skin. Use gloves, goggles and coveralls. In case of spillage on clothing, change clothing to prevent prolonged contact with skin. Wash contaminated clothing before reuse. Discard contaminated shoes. In case of accidental contact with skin, wash immediately with soap and water. In case of eye contact, flush thoroughly with plenty of water and call physician. If swallowed accidentally, do not induce vomiting. Seek medical attention immediately.

The user of this product is responsible for making its own evaluation and tests regarding the capabilities, safety, utility, suitability and application of the product, and assumes all risks and liabilities resulting from the use or application of the product, whether used alone or with other products. American Safety Technologies (herein referenced to as the COMPANY) warrants only that the product conforms to the specifications contained in product Technical Data Sheets published by the COMPANY, a copy of which is available to the user. If the product fails to conform to this warranty, the user shall return the product within 10 days of the purchase date with a note specifying the defect and the COMPANY will either replace the product or at its option, return the purchase price. EXCEPT AS EXPRESSLY PROVIDED IN THIS PARAGRAPH, THE COMPANY MAKES NO REPRESENTATIONS OR WARRANTIES OF ANY KIND, NATURE OR DESCRIPTION, EXPRESS OR IMPLIED, INCLUDING, WITHOUT LIMITATION, ANY WARRANTY OF MERCHANTABILITY OR FITNESS FOR ANY PARTICULAR PURPOSE, AND HEREBY DISCLAIMS THE SAME.

In no event shall the COMPANY be liable to the user of this product, whether in contract or in tort or under any other legal theory (including, without limitation, negligence), for damages which exceed the purchase price of the product, or for any indirect, incidental, consequential or similar damages, arising out of sale, use or application of the product, or for any claim made against the user by any other party, even if American Safety Technologies has been advised of the possibility of such claim.

130 Commerce Drive Montgomeryville, PA 18936 Phone: 800-631-7841 - 215-855-8450 - Fax: 215-855-4688